

# Deks Olje<sup>#2</sup> Deep Gloss Finish

The finishing part of the time-proven Deks Olje wood treatment system.



- Highlights the grain
- Easy maintenance
- No more sanding
- Rich deep gloss
- Economical



**Nothing surpasses the beauty of fine wood treated with Deks Olje. The preferred alternative to varnish.**

Every boat owner likes the satisfaction of seeing a gleaming new varnish job or the rich look of freshly oiled wood. But it is discouraging to see varnish looking dull or even peeling after just one season or oiled wood begin to darken in just a few months. **ENTER DEKS OLJE.**

**Deks Olje #2 is the finishing part of the time proven Deks Olje system.**

**Deks Olje #2** will give a deep rich gloss finish that is especially beautiful on teak and other exotic woods. It gives a stunning finish on cap rails, cockpit coamings, skylights, spars and other brightwork on boats both exterior and interior. It also look great on garden furniture.

**Deks Olje #2** is truly a boat owners dream come true, because it eliminates scraping, sanding and messy paint removers. After months of water duty under the extreme conditions of sun, salt and wind, Deks Olje's smooth, glossy surface can be renewed by scrubbing abraded and worn areas with soap and water, then simply recoating with Deks Olje #2 to match surrounding areas. **NO SANDING IS NECESSARY.**

One of the features of Deks Olje #2 is that it will not peel, blister or crack - unlike conventional wood finishes, such as varnish.

**Before applying Deks Olje #2 it is absolutely essential that the wood to be coated is first treated with the Deks Olje #1 saturator in order to achieve the desired and beautiful end result.**



HOW WOOD SHOULD BE TREATED

# Deks Olje<sup>#2</sup> Deep Gloss Finish

The finishing part of the time-proven Deks Olje wood treatment system.

Exterior  
Interior

### Surface Preparation

1. Apply Deks Olje #1 by the saturation method following directions on the can
2. Allow Deks Olje #1 to cure for 3 days
3. Clean the surface with a tack cloth

### Application

**DO NOT THIN.** Use a good quality varnish brush. For a Bristol finish apply 4-6 coats of Deks Olje #2 at the rate of one coat per day. Always wait 12-24 hours between coats. All coats should be applied within one month. No sanding is needed between coats.

Allow the coating to cure for 3 days before commissioning.

Do not apply Deks Olje when rain is imminent or late in the day when dew is expected. This may dull a newly set finish, or cause the coating to 'blush' although exposure to the sun usually removes this discoloration.

Do not apply Deks Olje in temperature below 8°C.

If you have to sand between coats to remove dust or other blemishes, make good the coats you have removed.

### Maintenance

The beauty of Deks Olje is that it needs so little maintenance. Periodic washing down with fresh water is all that is required. Should there be surface damage it can be easily repaired. Just use a fine grit sandpaper (#200-300) soaked in a little Deks Olje #1. Next day apply one or 2 coats of Deks Olje #2 at 12 hour intervals. There is no need to sand between coats and you will not see the mend when the coating is dry.

### Coverage


15m<sup>2</sup> per litre per coat on wood which has been properly treated with Deks Olje #1.



**Damaged varnish and teak oil lets water seep into the wood. Deks Olje penetrates and provides a rich, deep waterproof seal.**

DEKS OLJE #1  
SATURATOR

DEKS OLJE #2



OTHER TEAK OIL

TEAK OIL & VARNISH



Application Tools	Brush or roller
Application Temperature	5°-35°C
Drying Time	12-24 hours
Full Curing	3 days
Clean-up	Mineral spirits

**Available Sizes:** 1 litre, 4 litre, 10 litre.



For more information and assistance  
**FREECALL 1800 226 113**

**THE FLOOD COMPANY AUSTRALIA**

4 Nelson Avenue, Padstow, NSW 2211 Australia

Phone (+61) 2 9790 5158 Fax (+61) 2 9709 2604 Email [info@floodaustralia.com](mailto:info@floodaustralia.com)



visit our web site... [www.floodaustralia.net](http://www.floodaustralia.net)



HOW PAINT SHOULD BE TREATED